

PRODUCT DATA SHEET

Revision Date: 13/01

ATUREX® 340 Cycloaliphatic Amine Adduct

It is low viscosity with excellent color and color stability. It gives high-gloss, non-blushing films with good chemical resistance.

FEATURES

- Cure at low temperatures under damp conditions
- Good film properties
- Excellent color and color stability
- Good adhesion and very good chemical resistance

- Good water resistance
- Range of cure times and pot lives
- Very good heat-cure performance

APPLICATIONS

- Solvent-free and high-solids coatings
- Self-leveling flooring
- Mortars
- Grouts and lamination

PROPERTIES	TYPICAL QUALITY	SPECIFICATION
Specific Gravity, 25°C	1.02	1.02
Solids, %	-	-
AHEW	89	89
Use Level, phr	50	50
Gel Time, min/150g, 25°C	60	60
Thin Film Set Time, hr/25°C	6.0	6.0
Typical Cure Schedule	4 days	2-7 days at ambient
TYPICAL PROPERTIES		
Amine Value, mg KOH/g	325	315-345
Viscosity, mPa.s, 25°C	120	70-180
Color, Gardner	1	<2
HANDLING & STORAGE	In unopened, original containers at 2 - 40°C, (see Expiry date on original container)	
CN CODE	3908900000	
PACKAGING	In 210 liter tight head steel drums, net weight 190kg.	
HEALTH & SAFETY	Please refer to Material Safety Data Sheet	



Economic Development Zone, Yichun, Jiangxi, China.
Phone: +86 186 0795 0576 Tel: +86 795 3586166
Fax: +86 795 3586165 E-Mail: jackie@aturex.com
Web: www.aturex.com

Publication number 10086 – Revision Jan.2013

The information and statements herein are believed to be reliable, but not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification.