

# PRODUCT DATA SHEET

Revision Date: 13/01

## ATUREX® 395LC

### Modified Cycloaliphatic Amine Adduct

It is accelerated version of ATUREX 380 offering faster cure rate and hardness development.

#### FEATURES

- Cure at low temperatures under damp conditions
- Good film properties
- Excellent color and color stability
- Good adhesion and very good chemical resistance

- Good water resistance
- Range of cure times and pot lives
- Very good heat-cure performance

#### APPLICATIONS

- Solvent-free and high-solids coatings
- Adhesives
- Mortars
- Grouts and lamination

PROPERTIES	TYPICAL QUALITY	SPECIFICATION
Specific Gravity, 25°C	1.05	1.05
Solids, %	-	-
AHEW	95	95
Use Level, phr	50	50
Gel Time, min/150g, 25°C	30	30
Thin Film Set Time, hr/25°C	5.0	5.0
Typical Cure Schedule	4 days	2-7 days at ambient
<b>TYPICAL PROPERTIES</b>		
Amine Value, mg KOH/g	340	325-355
Viscosity, mPa.s, 25°C	500	300-700
Color, Gardner	1	<2
<b>HANDLING &amp; STORAGE</b>	In unopened, original containers at 2 - 40° C, (see Expiry date on original container)	
<b>CN CODE</b>	3908900000	
<b>PACKAGING</b>	In 210 liter tight head steel drums, net weight 190kg.	
<b>HEALTH &amp; SAFETY</b>	Please refer to Material Safety Data Sheet	



Economic Development Zone, Yichun, Jiangxi, China.  
Phone: +86 186 0795 0576 Tel: +86 795 3586166  
Fax: +86 795 3586165 E-Mail: [jackie@aturex.com](mailto:jackie@aturex.com)  
Web: [www.aturex.com](http://www.aturex.com)

Publication number 10086 – Revision Jan.2013

The information and statements herein are believed to be reliable, but not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification.